

11-24-00

Docket No. 4704

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Patent Application
 Commissioner for Patents
 Washington, D.C. 20231

Re: Inventor(s): Yuen, et al
 Title: Etching a Substrate in a Process Zone

JC914 U.S. PTO
 09/7/83
 11/21/00

Transmitted herewith is the patent application identified above, including:

☒ Specification, claims and abstract, totaling 34 pages.

drawings totaling 6 pages, X Formal Informal.

executed Declaration and Power of Attorney.

Information Disclosure Statement, PTO-1449 form, and copies of citations

Assignment of the invention to Applied Materials, Inc. and Assignment Recordation Cover Sheet

Post Card for return

FEE CALCULATION

Fee Items	Claims Filed	Included with Basic Fee	Extra Claims	Fee Rate	Total
1 Claims	54	- 20 =	34	x 18.00	\$612.00
pendent Claims	8	- 3 =	5	x 80.00	\$400.00
c Filing Fee				710.00	\$710.00
TOTAL FEES					\$1,722.00

☒ The Commissioner is hereby authorized to charge \$1722.00 to Deposit Account No. 50-1074.

☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 50-1074. A duplicate copy of this transmittal is enclosed.

☒ Please address all future correspondence to: **APPLIED MATERIALS, INC.**
Patent Department
P.O. Box 450A
Santa Clara, CA 95052

I hereby certify that this correspondence is being deposited with the United States Postal Service as express mail in an envelope addressed to:

Box Patent Application
 Assistant Commissioner for Patents
 Washington, D.C. 20231

Express Mail Receipt No. EL356915802US Date of Deposit 11-21-2000

By Robert W. Mulcahy Signature Robert W. Mulcahy

Respectfully submitted,

Robert W. Mulcahy
 Registration No. 25,436

United States Patent Application for:

ETCHING A SUBSTRATE IN A PROCESS ZONE

Inventors:

- 1) Stephen Yuen
a citizen of the United States of America,
2435 Ruth Cabral Way
Santa Clara, California 95050;
- 2) Mohit Jain
a citizen of India,
3301 Monroe Street, #3
Santa Clara, California 95051; and
- 3) Thorsten B. Lill
a citizen of Germany,
880 E. Fremont Ave. #634
Sunnyvale, California 94087.

Assignee: Applied Materials, Inc.
Entity: Large Entity
Docket No.: 4704/USA/ETCH/SILICON

I hereby certify that this correspondence is being deposited with the United State Postal Service as express mail in an envelope addressed to :

Box Patent Application
Commissioner for Patents
Washington, D.C. 20231

Express Mail Receipt No. EL356915802US Date of Deposit 11-21-2000
By BETH MULCAHY Signature Beth Mulcahy

ETCHING A SUBSTRATE IN A PROCESS ZONE

BACKGROUND

The invention relates to etching a substrate in a process zone.

5 In the manufacture of integrated circuits, active and passive devices are formed on a substrate, such as a semiconductor wafer, by alternately depositing and etching layers of dielectric, semiconducting, and conducting materials, such as silicon dioxide, polysilicon, and metal-containing materials. These layers may be etched to form a pattern of etched features in a predefined pattern of gates, vias, contact holes, trenches, and/or metal interconnect lines. Etching is typically performed using an energized etchant gas, such as a halogen-containing gas, as for example described in Silicon Processing for the VLSI Era, Vol. 1, Chapter 16, by Wolf and Tauber, Lattice Press, 1986, which is incorporated herein by reference.

10
15 The predefined pattern may be formed by providing photoresist over an underlying material to be etched. The photoresist may be patterned by lithography to expose portions of the underlying material. However, when photoresist is used it often is difficult to maintain the critical dimensions of the etched features. It is also difficult to obtain good etching selectivity for etching underlying material relative to the photoresist, especially when the underlying material is an oxide. In addition, while etching the underlying material, process conditions are generally selected to preserve the photoresist to prevent premature removal of the photoresist and also to reduce deposition of process residues on chamber or substrate surfaces. Furthermore, residual photoresist portions that are not etched by the etchant gases and which remain on the substrate after the etching process may need to be removed in a post processing step. Conventional photoresist removal processes, also known as stripping or ashing, are sometimes ineffective in removing all the resist from the substrate without overexposing a processed substrate to the energized stripping gas. In addition, resist removal processes compromise process throughput by adding a process step and a separate process chamber.

20
25
30

5 The process chambers used in processing a substrate are periodically cleaned to remove process residue deposits and contaminants that are formed on the surfaces in the chamber, otherwise these deposits may flake off and contaminate the substrate. In etching processes, after etching every 100 to 300 wafers, the chamber is often opened to the atmosphere and cleaned in a "wet-cleaning" process, in which an operator uses an acid or solvent to scrub off or dissolve accumulated etch residue on the chamber surfaces. After cleaning, the chamber is pumped down in a vacuum for 2 to 3 hours to outgas volatile species, and a series of etching runs are performed on dummy wafers until the chamber provides consistent etching properties. However, 10 the downtime of the etching chamber during the cleaning process can substantially increase the cost per substrate. Also, because the wet cleaning process is manually performed, the cleanliness of the chamber surfaces often vary from one cleaning session to another.

15 Therefore, it is desirable to be able to etch a substrate with improved critical dimension control and etching selectivity. It is further desirable to process the substrate with increased throughput. It is still further desirable to process a substrate in a substantially clean process chamber to reduce the possibility of contaminating the substrate. It is still further desirable to remove sufficient amounts of etch resistant material from the substrate without undesirably etching the substrate with the 20 energized gas.

SUMMARY

25 The present invention satisfies these needs. In one aspect of the invention, a substrate processing method comprises providing a substrate in a process zone, the substrate comprising etch resistant material over an underlying material, removing the etch resistant material in the process zone, and after the etch resistant material is removed, providing an energized process gas in the process zone to etch 30 the underlying material.

In another aspect of the invention, a substrate processing method comprises providing a substrate in a process zone, the substrate comprising a first and a second etch resistant material, providing an energized process gas in the

process zone to form apertures in the first etch resistant material, and removing the second etch resistant material in the process zone.

5 In another aspect of the invention, a substrate processing method comprises providing a substrate in a process zone, the substrate comprising etch resistant material, and removing the etch resistant material while detecting radiation emanating from the process zone.

10 In another aspect of the invention, a substrate processing method comprises providing a substrate in a process chamber, providing an energized process gas in the chamber to process the substrate, thereby depositing process residue on surfaces of the process chamber, providing an energized process gas in the chamber to simultaneously remove a material from the substrate and at least partially remove the process residue from the surfaces of the process chamber, and providing an
15 energized process gas in the chamber to further process the substrate.

20 In another aspect of the invention, a substrate processing method comprises providing a first substrate in a process chamber, providing an energized process gas to etch the first substrate, thereby depositing first residue on the surfaces of the process chamber, providing a second substrate in the process chamber, and providing an energized process gas to process the second substrate and simultaneously remove the first residue from the surfaces of the process chamber.

25 In another aspect of the invention, a substrate processing method comprises providing a first substrate in a process chamber, providing an energized process gas to etch the first substrate, thereby depositing first residue on the surfaces of the process chamber, providing a second substrate in the process chamber, and providing an energized process gas to at least partially remove the first residue from the surfaces of the process chamber, and removing the second substrate from the
30 chamber.

In another aspect of the invention, a substrate processing method comprises providing a substrate in a process chamber, providing a first energized process gas to etch a material on the substrate, thereby depositing residue on the

surfaces of the process chamber, providing a second energized process gas to remove substantially all of the residue deposited from the surfaces of the process chamber, and removing the second substrate from the chamber.

5 In another aspect of the invention, a substrate processing method comprises providing a substrate in a process zone, the substrate comprising resist material over mask material, providing an energized process gas in the process zone to form apertures in the mask material, providing an energized process gas in the process zone to remove the resist material, and providing an energized process gas in the process zone to etch a layer under the mask material.

DRAWINGS

These features, aspects, and advantages of the present invention will become better understood with regard to the following description, appended claims, and accompanying drawings which illustrate exemplary features of the invention. However, it is to be understood that each of the features can be used in the invention in general, not merely in the context of the particular drawings, and the invention includes any combination of these features, where:

20 Figure 1 is a schematic sectional side view of a process chamber with a process zone adapted to process a substrate according to the present invention;

25 Figures 2a through 2d are schematic sectional side views of a substrate that is processed according to one version of the present invention;

Figures 3a through 3c are schematic sectional side views of a substrate that is processed according to another version of the present invention;

30 Figures 4a through 4e are schematic sectional side views of a substrate that is processed according to yet another version of the present invention;

Figure 5 is a schematic sectional side view of a substrate processing apparatus and endpoint detection system according to the present invention; and

Figure 6 is an illustrative block diagram of a structure of a computer program suitable for operating the chamber and monitoring a process performed therein.

DESCRIPTION

The present invention relates to processing a substrate in an apparatus, for example to fabricate integrated circuits on the substrate and is particularly useful for processing layers, such as etch resistant, silicon-containing, metal-containing, dielectric, and/or conductor layers on the substrate. Although the process is illustrated in the context of etching one or more of the layers on the substrate, the present invention can be used in other processes such as chemical vapor deposition (CVD), physical vapor deposition (PVD), evaporation, post etch treatment, and other substrate fabrication processes and should not be limited to the examples provided herein.

An apparatus **100** suitable for processing a substrate **105** according to the principles of the present invention comprises a process chamber **110**, such as a "DPS" chamber, schematically illustrated in Figure 1, and commercially available from Applied Materials Inc., Santa Clara, California. The particular embodiment of the apparatus **100** shown herein is suitable for processing substrates **105**, such as semiconductor wafers, and may be adapted by those of ordinary skill to process other substrates **105**, such as flat panel displays, polymer panels, or other electrical circuit receiving structures. The apparatus **100** is provided only to illustrate the invention, and should not be used to limit the scope of the invention or its equivalents to the exemplary embodiments provided herein. The apparatus **100** may be attached to a mainframe unit that contains and provides electrical, plumbing, and other support functions for the apparatus **100**. Exemplary mainframe units compatible with the illustrative embodiment of the apparatus **100** are currently commercially available as the Precision 5000™ systems from Applied Materials, Inc., of Santa Clara, California. The multichamber system has the capability to transfer a wafer between its chambers without breaking the vacuum and without exposing the wafer to moisture or other contaminants outside the multichamber system. An advantage of the multichamber system is that different chambers in the multichamber system may be used for

different purposes in the entire process. For example, one chamber may be used for etching a substrate **105**, another for the deposition of a metal film, another may be used for rapid thermal processing, and yet another may be used for depositing an anti-reflective layer. The process may proceed uninterrupted within the multichamber system, thereby preventing contamination of substrates **105** that may otherwise occur when transferring substrates **105** between various separate individual chambers (not in a multichamber system) for different parts of a process.

Generally, the apparatus **100** comprises a chamber **110** comprising walls typically fabricated from metal or ceramic materials. Metals commonly used to fabricate the chamber **110** include aluminum, anodized aluminum, "HAYNES 242," "Al-6061," "SS 304," "SS 316," and INCONEL, of which anodized aluminum is preferred. In the embodiment shown, the chamber **110** comprises a wall which may comprise a ceiling **115**, sidewalls **117**, and a bottom wall **118**. The ceiling **115** may comprise a substantially arcuate portion, or in other versions, the ceiling **115** may comprise a dome, substantially flat, or multi-radius shaped portion. The chamber **110** typically comprises a volume of at least about $5,000 \text{ cm}^3$, and more typically from about $10,000$ to about $50,000 \text{ cm}^3$. In operation, process gas is introduced into the chamber **110** through a gas supply **120** that includes a process gas source **122**, conduits **124** having flow control valves **126**, and gas outlets **128** around a periphery of the substrate **105** which may be held on a support **130**. As an alternative to the configuration shown in Figure 1, the process gas may be introduced through a showerhead (not shown) mounted on or near the ceiling **115** of the chamber. Spent process gas and etchant byproducts are exhausted from the chamber **110** through an exhaust system **132** which includes a pumping channel **134** that receives spent process gas, a throttle valve **136** to control the pressure of process gas in the chamber **110**, and one or more exhaust pumps **138**. The exhaust system **132** may also contain a system for abating undesirable gases from the exhaust.

The process gas is energized to process the substrate **105** by a gas energizer **150** that couples energy to the process gas in the process zone **155** of the chamber **110** (as shown) or in a remote zone upstream from the chamber **110** (not shown). In one version, the gas energizer **150** comprises an antenna **160** comprising one or more inductor coils which may have a circular symmetry about the center of

the chamber **110**. Typically, the inductor coils **160** comprises solenoids having from about 1 to about 20 turns. A suitable arrangement of solenoids is selected to provide a strong inductive flux linkage and coupling to the process gas. When the antenna **160** is positioned near the ceiling **115** of the chamber **110**, the adjacent portion of the ceiling may be made from a dielectric material, such as silicon dioxide, which is transparent to RF or electromagnetic fields. An antenna power supply **165** provides, for example, RF power to the antenna **160** at a frequency of typically about 50 KHz to about 60 MHz, and more typically about 13.56 MHz; and at a power level of from about 100 to about 5000 Watts. An RF match network may also be provided.

In one version, the gas energizer **150** may also or alternatively comprise process electrodes that may be powered by a power supply **157** to energize or further energize the process gas. Typically, the process electrodes include one electrode in a wall, such as a sidewall **117** or ceiling **115** of the chamber **110** that may be capacitively coupled to another electrode, such as an electrode in the support **130** below the substrate **105**. The electrode may comprise a dielectric ceiling **115** that serves as an induction field transmitting window that provides a low impedance to an RF induction field transmitted by the antenna **160** above the ceiling **115**. Suitable dielectric materials that can be employed include materials such as aluminum oxide or silicon dioxide. Generally, the electrodes may be electrically biased relative to one another by an electrode voltage supply (not shown) that includes an AC voltage supply for providing an RF bias voltage. The RF bias voltage may comprise frequencies of about 50 kHz to about 60 MHz, and is preferably about 13.56 MHz, and the power level of the RF bias current is typically from about 50 to about 3000 watts. Alternatively or additionally, the gas energizer **150** may comprise a microwave gas activator (not shown) that transmits microwaves to the gas to energize the gas.

The support **130** may comprise an electrostatic chuck **170** which comprises a base **172** for supporting a dielectric **174** which comprises a portion **176** which at least partially covers a chucking electrode **178** and which may include a substrate receiving surface **180**. The electrode **178** may also serve as one of the process electrodes discussed above (as shown in Figure 5). Alternatively, the base **172** may serve as a process electrode (as shown in Figure 1). The base **172** may have channels (not shown) through which heat transfer fluid is circulated to heat or

cool the substrate **105**. The base **172** may be generally shaped and sized to match the shape and size of the substrate **105** to maximize heat transfer to the substrate. For example, for a substrate **105** having a circular or disk shape, the base **172** may be of generally right cylindrical shape. In one version, the base **172** comprises an electrically conducting material, such as aluminum, and is surrounded by an insulating shield or jacket made of, for example, an insulating polymeric or ceramic material, such as quartz. In one version, the base **172** may be electrically biased by a voltage supply.

The dielectric **174** of the support **130** or electrostatic chuck **170** isolates, or partially isolates, the electrode **178** from the substrate **105** and the energized gas in the chamber **120**. In an alternative configuration, the dielectric **174** may cover the base **172** which serves as the electrode. As shown, the dielectric **174** comprises a monolith in which the electrode **178** is embedded. The dielectric **174** may be made from a dielectric material that is resistant to erosion by the gas or plasma and capable of withstanding high temperatures. Suitable dielectric materials include, for example, ceramic materials, such as Al_2O_3 , AlN , BN , Si , SiC , Si_3N_4 , TiO_2 , ZrO_2 , and mixtures and compounds thereof, and polymeric materials such as polyimide, polyamide, polyetherimide, polyketone, polyetherketone, polyacrylate, fluoroethylene, or mixtures thereof or the like. The thickness of the portion of dielectric material **176** overlying the electrode **178** is typically from about 100 micrometers to about 1000 micrometers.

The support **130** or electrostatic chuck **170** may also comprise temperature controlling devices. For example, the dielectric **174** may comprise one or more conduits (not shown) extending therethrough, such as for example, a gas conduit provided to supply heat transfer gas from a heat transfer gas supply (not shown) to an interface between the surface **180** of the dielectric **174** and the substrate **105**. The heat transfer gas, typically helium, promotes heat transfer between the substrate **105** and the support **130** or electrostatic chuck **170**. Other conduits may, for example, allow lift pins (not shown) to extend through the dielectric **174** for loading or unloading of the substrate **105** by a lift mechanism. The support **130** may also comprise a heating system **182**. In one version the heating system may comprise a heating element **184**, such as a resistively heated plate, wire, mesh or coil,

through which a current may pass to cause the element to increase in temperature. A heater power supply **186** may be provided to provide a heating voltage to the heating element **184** under the control of a system controller.

5 The electrode **178** may be capable of generating an electrostatic charge for electrostatically holding the substrate **105** to the support **130** or electrostatic chuck **170**. A DC voltage supply **188** provides the chucking voltage to the electrode **178** through an electrical connector **190** such as a banana jack inserted through the dielectric **174**. The DC chuck power supply **188** typically provides a DC chuck
10 voltage of 250 to 2000 volts to the electrode **178**. The voltage supply **188** can also include a system controller for controlling the operation of the electrode **178** for chucking or dechucking the substrate **105**.

15 In another chamber embodiment (not shown), the energized gas, such as a capacitively generated plasma, may be substantially confined to the process zone **155** immediately above the surface of the substrate **105** by a magnetic field (not shown) that is substantially perpendicular to the plane of the substrate. The magnetic field is generated by permanent magnets or electromagnets (neither shown) adjacent to the chamber **110**, as for example, described in U.S. Patent No. 4,842,683, issued
20 June 27, 1989, which is incorporated herein by reference.

Processing a Substrate

25 The apparatus **100** illustrated herein can be used to process material on a substrate **105**, for example to etch material from the substrate **105**; remove contaminant deposits or residues deposited on surfaces in the chamber **110**, such as on the surfaces of walls of the chamber **110** and the surfaces of components in the chamber **110**; perform post processing treatment of a substrate **110**, or the like. For example, in one version, the apparatus **100** may be used to etch a substrate **105**,
30 such as a substrate **105** comprising one or more layers of material. Such layers are often superimposed on one another and may comprise dielectric layers comprising, for example, silicon dioxide, undoped silicate glass, phosphosilicate glass (PSG), borophosphosilicate glass (BPSG), Si_3N_4 , or TEOS deposited glass; semiconducting layers comprising, for example, silicon-containing layers such as polysilicon or a

silicon compound; and conductive layers such as metal-containing layers comprising, for example, aluminum, copper, or metal silicide such as tungsten silicide and cobalt silicide. Suitable etchant gases for etching layers on the substrate **105**, include for example, HCl, BCl₃, HBr, Br₂, Cl₂, CCl₄, SiCl₄, SF₆, F, NF₃, HF, CF₃, CF₄, CH₃F, CHF₃, C₂H₂F₂, C₂H₄F₆, C₂F₆, C₃F₈, C₄F₈, C₂HF₅, C₄F₁₀, CF₂Cl₂, CFCI₃, O₂, N₂, He, and mixtures thereof. The etchant gas is selected to provide high etch rates, and highly selective etching of the particular layers or materials that are being etched. When multiple layers are sequentially etched, first, second, third, etc., etchant gas compositions may be sequentially introduced into the chamber to etch each particular layer.

To etch one or more of the layers on the substrate **105** in the process chamber **110**, process gas comprising etchant gas is introduced from the gas supply **120** into the process zone **155** and energized by the gas energizer **150** to form an energized gas. The gas may be energized by inductively and/or capacitively coupling energy into the process zone **155** of the chamber **110**, or by applying microwaves thereto or to an etchant gas in a remote zone of a remote chamber (not shown) that is at a location remote from the process zone **155**. By "energized process gas" it is meant that the process gas is activated or energized so that one or more dissociated species, non-dissociated species, ionic species, and neutral species are excited to higher energy states in which they are more chemically reactive. In the version shown in Figure 1, the process gas is energized by applying an RF source current to the inductor antenna **160** adjacent to the chamber **110** and optionally by also applying an RF bias voltage to process electrodes. The energized etchant gas etches one or more layers on the substrate **105** to form volatile gaseous species that are exhausted from the chamber **110** by exhaust system **132**.

An example of a substrate **105** which may be etched in accordance with the present invention is shown in Figure 2a. In the version of Figure 2a, the substrate **105** comprises etch resistant material **210** overlying a workpiece **220**, which may comprise one or more layers of material. The etch resistant material **210** is resistant to etch by process gas which is introduced into a process zone **155** under process conditions selected to etch into and/or through an underlying material, such as the workpiece **220** which may be a wafer or layers on a wafer as will be discussed. The

etch resistant material **210** may be patterned to expose portions of the underlying material for etching. For example, the etch resistant material **210** may comprise resist material **230**, such as polymeric or organic resist. The resist material **230** may be patterned by conventional photolithographic methods or may be patterned by etching the resist material **230** in a process chamber **110**. In one version, the etch resistant material **210** comprises an organic, polymeric photoresist that is transparent to ultraviolet light frequencies and does not block incident light beams having wavelengths in the ultraviolet range. Alternatively or additionally, the etch resistant material **210** may comprise mask material **240** comprising, for example, a dielectric material or hard mask, such as silicon oxide, TEOS, silicon nitride, or equivalents. In the version of Figure 2a, the substrate **105** comprises an etch resistant material **210** comprising a patterned resist material **230** over a mask material **240**.

The mask material **240** may be patterned by providing the substrate in a process zone **155** and introducing process gas into the process zone **155** to etch into the exposed portion **250** of the mask material **240** to form apertures **245** therein in accordance with the pattern of the resist material **230**. For example, the process gas may comprise a mask material etching gas comprising one or more gases selected to etch into the mask material **240**. In one version, a process gas comprising a mask material etching gas is introduced to etch into and through the mask material **240** to open the mask and form the apertures **245**, as shown in Figure 2b, to expose a portion **260** of the workpiece **220**. In one version, the mask material etching gas comprises a halogen containing gas, such as a fluorine containing gas. For example, the mask etching gas may comprise one or more of HCl, BCl₃, HBr, Br₂, Cl₂, CCl₄, SiCl₄, SF₆, F₂, NF₃, HF, CF₃, CF₄, CH₃F, CHF₃, C₂H₂F₂, C₂H₄F₆, C₂F₆, C₃F₈, C₄F₈, C₂HF₅, C₄F₁₀, CF₂Cl₂, CFCI₃ or equivalents. In one particular version, the mask material comprises one or more of silicon oxide, TEOS, and silicon nitride and the mask material etching gas comprises one or more of CF₄, C₂F₆, SF₆, and NF₃. The process gas may further comprise a carrier or inert gas, such as one or more of Ar and He to aid in controlling etch sputtering and/or dilution.

The resist material **230** may be removed from the substrate by introducing an energized stripping gas into the process zone **155**. The stripping gas may comprise one or more of O₂, N₂, H₂O, NH₃, CF₄, C₂F₆, CHF₃, C₃H₂F₆, C₂H₄F₂, or

CH₃F. A suitable stripping gas for stripping the polymeric resist comprises (i) oxygen, and (ii) an oxygen activating gas or vapor, such as nitrogen gas, water vapor, or fluorocarbon gas, the fluorocarbon gases including any of those listed above. The oxygen activating gas increases the concentration of oxygen radicals in the stripping gas. In one version, the stripping gas comprises oxygen and nitrogen in a volumetric flow ratio of about 1:2 to about 200:1, and more preferably from about .8:1 to about 12:1, and most preferably about 1:1. For a 5000 cm³ process chamber **110**, a suitable gas flow rate comprises about 100 sccm of O₂ and about 100 sccm of N₂. The substrate **105** may be exposed to the stripping gas for a period of time of from about 10 seconds to about 1000 seconds, and more preferably for about 60 seconds. A single stripping step may be performed or multiple stripping steps may be performed, as discussed in U.S. Patent No. 5,545,289, which is incorporated herein by reference in its entirety.

In one version of the invention, the resist material **230** may be removed from the substrate **105** before the workpiece **220** is etched. For example, following forming the apertures **245** to pattern the mask material **240**, the resist material **230** may be removed, as shown in Figure 2c, leaving patterned mask material **240** over the workpiece **220**. The resist material **230** may be removed by exposing the resist material **230** or remnant resist material to an energized stripping gas, for example. After removal of the resist material **230**, the exposed portions **260** of the workpiece **220** may be etched by introducing etchant gas, for example halogen-containing gas, to form features **270**, such as apertures that may be used to form, for example, gates, vias, contact holes, trenches, and/or metal interconnect lines, as shown in Figure 2d.

Removing the resist material **230** before etching features **270** in the workpiece **220** has several advantages over post-etch removal of the resist material **230**. For example, when the resist material **230** is removed and an underlying mask material **240** serves as the etch resistant material **210** for defining the pattern that will be etched into the workpiece **220**, an improved etch of the workpiece **220** may be performed. The mask material **240** is often more resistant to the etchant gas introduced to etch the workpiece **220** than the resist material **230** and thereby provides better selectivity to etching the underlying material. This allows for improved

critical dimension (CD) control. In addition, by eliminating the necessity to preserve the resist material **230**, more aggressive workpiece etchant process conditions may be utilized, thereby allowing for an increased etch rate of the workpiece **220**. Also, when resist material **230** is present during etching of a silicon-containing material in the workpiece **220**, partial removal or sputtering of the resist material **230** and etchant byproducts from the etching of the workpiece **220** can create a sandwich type of residue that can deposit on the substrate **105** and/or on surfaces of the chamber **110**. The sandwich type deposit, such as layered silicon oxide and polymer, are difficult to clean and potentially can flake-off and affect the quality of the processed substrate **105**. By removing the resist material **230** before etching the workpiece **220**, the formation of the sandwich type deposits during etching of the workpiece **220** can be substantially avoided.

In one version, the resist material **230** is removed from the substrate **105** and the workpiece **220** is etched in the same process zone **155**. The resist material **230** may also be removed before the workpiece **220** is etched. Removing resist material **230** and etching the workpiece **220** in the same process zone improves process throughput. For example, by not transferring the substrate from an etching chamber to a resist removal chamber, throughput can be substantially increased. Additionally, eliminating the necessity of a resist removal chamber in a multichamber system can provide space for parallel processing of substrates, further increasing throughput. In another version, The mask material **240** is patterned and the resist material **230** is removed in the same process zone **155**. This version also increases throughput and provides additional processing space in a multichamber system by avoiding the need to have a separate mask material **240** etching chamber and resist material **230** removal chamber.

In another version, apertures are formed in the mask material **240**, the resist material **230** is removed, and the workpiece **220** is etched in the same process zone **155**. This version further increases throughput by using a single chamber instead of three chambers and provides even more utilizable space in a multichamber system. In addition, performing all three of these steps in a single process zone **155** provides unexpected results. For example, among the unexpected advantages are

improved chemistry compatibilities, synergistic chamber cleaning treatment, simplified post processing treatment, and enhanced etch performance.

By using a single process zone **155** to form apertures in the mask material **240**, remove resist material **230**, and etch the workpiece **220**, the process conditions may be selected to result in simultaneous chamber cleaning and substrate processing. For example, when mask material **240**, which may comprise silicon oxide, silicon nitride, or TEOS, is opened in a mask patterning process gas, polymeric residue may be formed on the substrate and on surfaces **275** in the chamber **110**. These surfaces **275** include the surfaces of walls of the chamber **110** and the surfaces of components within or near the chamber **110**. The process residue may be removed during the removal of the resist material **230**. For example, the process gas comprising stripping gas may be introduced under process conditions selected to simultaneously remove the resist material **230** from the substrate **105** and remove the residue deposited on the chamber surfaces **275** during etching of the mask material **240**. This provides a chamber **110** with surfaces **275** substantially devoid of residue when etching of the workpiece **220** is initiated. During etching of the workpiece **220**, particularly during etching of silicon-containing layers or material in or on the workpiece **220**, etchant residue may be deposited on the surfaces **275** in the chamber **110**. The etchant residue may comprise, for example, silicon oxide. Thus, when the substrate **105** is removed from the chamber **110**, and a second substrate **105** is provided in the process zone **155** and process gas comprising mask material etching gas is introduced to open the mask material **240** of the second substrate **105**, the mask material etching gas may be introduced under process conditions selected to also remove residue on the chamber surfaces **275** that was generated during the etching of the workpiece **220** of the previously processed substrate **105**. The residue then formed during etching of the mask material **240** is deposited directly on the chamber surfaces **275** rather than on top of previously formed etchant residue, and this residue is then removed as discussed above. This cyclical etching and cleaning process may continue throughout processing of a batch of substrates **105** with the mask material patterning step simultaneously cleaning etchant residue formed during processing of a previous substrate, the resist material removal step simultaneously removing residue formed during mask patterning of the present substrate. Thus, a

consistently clean chamber is continuously present for the initiation of etching of each substrate **105** in the batch of substrates.

In one version, a two-step mask material etch may be performed. For example, a first step may comprise exposing mask material **240** to process gas substantially absent a polymer forming gas and the second step may comprise exposing the mask material **240** to process gas comprising a polymer forming gas. In one particular version, the first mask material etchant gas may comprise a fluorine-containing gas, for example, in one version, the first mask material etchant gas comprises one or more of CF_4 , C_2F_6 , NF_3 , and SF_6 , and the second mask material etchant gas may comprise one or more of CHF_3 , CH_2F_2 , and CH_3F , with or without one or more of CF_4 , C_2F_6 , NF_3 , and SF_6 . The first or second mask material etchant gases may also comprise an inert or carrier gas, such as Ar, He, or N to aid in controlling sputtering and/or dilution. In this version, the etchant residue formed during processing of a previous substrate may be cleaned from the chamber surfaces **275** before polymeric residues are formed and deposited thereon. This can result in easier removal of the etchant deposits. Sandwich deposits comprising a layer of silicon-containing etchant residue and a layer of polymer can be difficult to clean and can result in flaking during substrate processing that can affect the quality of the processing. By first introducing a non-polymerizing mask etching gas, the mask material **240** may be etched and the etchant residue may be cleaned from the chamber surfaces **275** before the polymeric residue is formed and deposited on the chamber surfaces **275**. It is advantageous to use the mask material etchant gas comprising polymer forming gas because it aids in etch process performance.

Another advantage of performing the mask material **240** patterning step, the resist material **230** removal step, and the workpiece **220** etching step in the same process zone **155** is that post processing treatment of the substrate **105** may be simplified. For example, the etch resistant material **210** may, in one version, comprise an anti-reflective coating (ARC), material **280** between the resist material **230** and the mask material **240**, as shown in Figure 3a. Anti-reflective coating material, such as SiON, or SiN, assists in photolithographic processes. As shown in Figure 3b, after the mask material **240** has been opened and the resist material **230** has been removed, a top layer of ARC material **280** remains on the substrate. Typically, the ARC material

280 is removed from the substrate in a separate post processing treatment step. However, in one version of the invention, the workpiece **220** may be etched and the ARC material **280** may be simultaneously removed by exposing the workpiece **220** and the ARC material **280** to process gas comprising etching gas under process conditions selected to etch into the workpiece **220** and remove the ARC material **280**, as shown in Figure 3c. In one version, the process gas comprises a fluorine-containing gas, such as CF_4 , and a halogen-containing gas, such as Cl_2 and, optionally nitrogen or argon. The resulting processed substrate **105** does not need a separate ARC material removal step in another process chamber.

One particular version of the invention is shown in Figures 4a-4e. This version is merely exemplary and is not intended to limit the invention. As shown in Figure 4a, a substrate **105** that may be processed in accordance with the present invention may include etch resistant material **210** overlying a workpiece **220**. The etch resistant material may comprise resist material **230**, such as photoresist, and mask material **240**, such as silicon oxide, TEOS, or silicon nitride, with anti-reflective material **280**, such as TiN, silicon oxynitride, silicon nitride, or organic anti-reflective material, therebetween. The workpiece **220** may comprise a base **290**, such as a wafer comprising silicon or a compound semiconductor, such as gallium arsenide, which may have doped regions. A semiconducting or conducting material **300**, for example a silicon-containing layer such as doped or undoped polysilicon or a silicon compound such as metal silicide overlies the base **290**. Between the semiconducting or conducting material **300**, a gate oxide material **310** may be provided. The gate oxide material may comprise an oxide material, such as silicon oxide, having a thickness of from about 10 Å to about 300 Å. Other versions of substrates **105** may alternatively be processed. For example, one or more of the above described layers may be removed and/or a metal containing layer or a diffusion barrier layer, comprising for example one or more of Ti, TiN, Ta, TaN, W, and WN may be provided.

Table 1 summarizes an example of process conditions including process gas compositions which may be used to process the substrate **105** of Figure 4a and clean the process chamber **110** in accordance with one version of the present invention. After providing the substrate **105** in the process zone **155**, an anti-reflective coating etch step comprises providing energized process gas comprising

reactive and non-reactive gas, such as CF_4 and Ar, respectively, in the process zone **155** to etch the anti-reflective coating **280**, if present. In one version, the volumetric flow ratio of non-reactive to reactive gas is from about 0:1 to about 5:1, more preferably from about 1:1 to about 2:1, and most preferably about 1.5:1. The mask material **240** may be etched in two steps. A first mask material etch step comprises providing energized process gas comprising reactive and non-reactive gas, such as CF_4 and Ar, respectively, in the process zone **155** to etch the mask material **240** and to remove etchant residue that may have been formed during the processing of previous substrates. In one version, the volumetric flow ratio of non-reactive to reactive gas is from about 0:1 to about 5:1, more preferably from about 1:1 to about 2:1, and most preferably about 1.5:1. A second mask material etch step comprises providing energized process gas comprising reactive gas and non-reactive gas in the process zone **155** to further etch the mask material **240**. In one version, the reactive gas comprises a polymer generating gas, such as CHF_3 , CH_2F_2 , or CH_3F . Optionally, an additional reactive gas, such as CF_4 , may be provided. The volumetric flow ratio of non-reactive to reactive gas may be from about 0:1 to about 5:1, more preferably from about 1:1 to about 2:1, and most preferably about 1.5:1. Figure 4b shows a substrate **105** with the mask material **240** etched to form a patterned mask layer. The next step comprises removing remnant resist material **230**, and optionally removing polymeric residue on the chamber surfaces **275** formed during etching of the mask material **240**, by providing an energized stripping gas, such as O_2 and N_2 in a volumetric flow ratio of oxygen to nitrogen of about 1:0 to about 1:5, more preferably from about 2:1 to about 1:2, and most preferably about 1:1, or other stripping gas as discussed above. The mask material **240** may then serve as etch resistant material **210** to form a pattern in the underlying material, as shown in Figure 4c.

Table 1

Material	Process Gas Flow Ratio	Source Power (Watts)	Bias Power (Watts)	Pressure (mTor)	Temperature (°C)
Anti-reflective Coating Etch	3/2 Ar/CF ₄	600	150	4	50
Mask Material First Etch	3/2 Ar/CF ₄	600	150	4	50
Mask Material Second Etch	6/1/3 Ar/CF ₄ /CHF ₃	600	150	4	50
Resist Stripping	1/1 O ₂ /N ₂	1000	100	150	50
Metal Silicide Etch	2/2/1 CF ₄ /Cl ₂ /N ₂	400	75	4	50
Polysilicon First Etch	60/1 HBr/O ₂	300	60	15	50
Polysilicon Second Etch	72.5/1 HBr/O ₂	450	120	65	50

The workpiece **220** may then be etched in the process zone **155**. The semiconducting or conducting material **300** may comprise a metal silicide layer and/or a polysilicon layer. A metal silicide layer, such as WSi, may be etched by providing an energized process gas comprising non-reactive gas and reactive gas in a volumetric flow ratio of from about 0:1 to about 4:1, more preferably from about 0:1 to about 1:1, and most preferably about 1:4. The reactive gas may comprise, for example, one or more of the earlier mentioned etchant gases, such as one or more of CF₄, C₂F₆, NF₃, SF₆, Cl₂, Br₂, HBR, and HCl. The non-reactive gas may comprise N₂, Ar, or the like. In one version, a polysilicon layer may be etched by providing an energized process gas comprising a halogen-containing gas, such as one or more of HBr, HCl, Br₂, Cl₂, CF₄, NF₃, and SF₆ and optionally an oxygen-containing gas, such as one or more of O₂, O₃, and He-O₂. In one version, the polysilicon layer may be etched in a two steps, such as shown in Table 1, to provide controlled etch feature shape, as desired. As shown in Figures 4d and 4e, as the semiconducting or conducting material **300** is being etched, the ARC material **280** may be removed.

Since the workpiece **220** is not susceptible to the energized stripping gas used to remove the resist material **230**, process conditions can be selected to remove the resist material **230** at a high rate. For example, a bias power of from about 20 watts to about 500 watts, more preferably from about 100 watts to about 200 watts, and most preferably about 100 watts, can be applied during the resist material removal. The bias power has been shown to aid in sputtering the resist

material **230** or other residue on the substrate **105**. Additionally, the chamber pressure can be increased to at least about 4 mTorr, and more preferably at least about 100 mTorr, to help facilitate the resist removal by increasing oxygen concentration. To further increase the resist material removal rate, the substrate **105** can be heated, such as by shutting off the circulation of cooling fluid in the support **130**, to a temperature of at least about 100 degrees C. The substrate **105** may then be cooled down to etch the workpiece **220**.

To remove sufficient amounts of the resist material **230** without overexposing the substrate **105** to energized stripping gas, the apparatus **100** and chamber **110** may comprise a process monitoring system **410** which may include an endpoint detection system to detect the occurrence of an endpoint of, for example, resist material removal, as shown in Figure 5. Endpoint detection methods are used to measure the endpoint of a process to prevent over processing of a material by stopping or changing the process conditions when an endpoint is detected. Endpoint measurement techniques include, for example, plasma emission analysis, interferometry, and ellipsometry, which detect radiation emanating from the chamber **110**. Plasma emission analysis involves analyzing the emission spectra of energized gas in the process zone **155** to determine a change in chemical composition that corresponds to a change in the chemical composition of the material being etched, as disclosed in U.S. Patent No. 4,328,068 which is incorporated herein by reference in its entirety. Optical emission detection for endpoint determination is also discussed in Chapter 16, of Silicon Processing for the VLSI Era, Volume 1: Process Technology, by Stanley Wolf et al., Lattice Press (1986), which is incorporated herein by reference in its entirety. The present invention is useful for monitoring events, such as events related to an endpoint, in an apparatus via a radiation measuring technique.

In the version shown in Figure 5, the chamber **110** comprises a process monitoring system **410** to monitor the process being performed on the substrate **105**. The process monitoring system **410** comprises a radiation source **415** that may be outside or inside the chamber **110**. The radiation source **415** may provide radiation such as ultraviolet (UV), visible or infrared radiation; or it may provide other types of radiation such as X-rays. The radiation source **410** may comprise, for example, an

emission from an energized gas, such as a plasma, generated inside the chamber **110**, the plasma emission being generally multispectral, i.e., providing radiation having multiple wavelengths extending across a spectrum. The radiation source **410** may also be positioned outside the chamber **110** so that a radiation beam **420** may be transmitted from the source **415** through a window **425** and into the chamber **110**. The radiation source **415** may also provide radiation having predominant wavelengths, or a single wavelength, such as monochromatic light, for example, a He-Ne or Nd-YAG laser. Alternatively, the radiation source **415** may provide radiation having multiple wavelengths, such as polychromatic light, which may be selectively filtered to a single wavelength. Suitable radiation sources **415** for providing polychromatic light include Hg discharge lamps that generate a polychromatic light spectrum having wavelengths in a range of from about 180 to about 600 nanometers, arc lamps such as xenon or Hg-Xe lamps and tungsten-halogen lamps, and light emitting diodes (LED).

The process monitoring system **410** further comprises a radiation detector **430** for detecting radiation emanating from the chamber **110**. For example, the emanating radiation may be from a plasma emission or may be radiation **435** reflected by the substrate **105**. The radiation detector **430** may comprise a radiation sensor, such as a photovoltaic cell, photodiode, photomultiplier, or phototransistor, which provides an electrical output signal in response to an emission spectra from the plasma or a measured intensity of reflected radiation **435**, for example. The signal may comprise a change in the level of a current passing through an electrical component or a change in a voltage applied across an electrical component. A suitable system for coupling the radiation detector **430** to the chamber **110** comprises a fiberoptic cable **440** leading to the sensor of the radiation detector **430**.

Optionally, a lens assembly **445** may be used to focus radiation emitted by the plasma onto the radiation detector **430**, to focus a radiation beam **420** emitted by the radiation source **415** onto the substrate **105**, or to focus a radiation beam **435** reflected back from the substrate **105** onto the sensor of the radiation detector **430**. For example, for a radiation source **415** comprising a Hg-discharge lamp located outside the chamber **110**, the lens assembly **445** may comprise a plurality of convex

lenses **446** that may be used to focus a radiation beam **420** from the lamp, through the window **425**, and as a beam spot **450** on the substrate **105**. The area of the beam spot **450** should be sufficiently large to provide an accurate measurement of the surface topography of the substrate **105**. The lenses may also be used to focus reflected radiation **435** back onto the sensor of the radiation detector **430** in the reverse direction or may be used to focus radiation from the energized gas to the radiation detector **430** which is especially useful when the radiation source **415** is an emission spectra from a plasma.

The chamber **110** and monitoring system **410** may be operated by a controller **460** that executes a computer-readable process control program on a computer system **470** comprising a central processor unit (CPU) **475**, such as for example a 68040 microprocessor, commercially available from Synergy Microsystems, California, or a Pentium Processor commercially available from Intel Corporation, Santa Clara, California, that is coupled to a memory and peripheral computer components. The memory comprises a computer-readable medium having the computer-readable program **480** embodied therein. Preferably, the memory includes a hard disk drive **485**, a removable media drive such as a floppy disk drive **490**, a ZIPTM drive, or a CD recordable drive, and random access memory **495**. The computer system further comprises a controller interface **500** which may comprise plurality of interface cards including, for example, analog and digital input and output boards, interface boards, and motor controller boards. The interface between an operator and the controller **460** can be, for example, via a display **510** and a light pen **515**. The light pen detects light emitted by the monitor with a light sensor in the tip of the light pen. To select a particular screen or function, the operator touches a designated area of a screen on the monitor and pushes the button on the light pen. Typically, the area touched changes color, or a new menu is displayed, confirming communication between the user and the controller **460**.

Computer-readable programs such as those stored on other memory including, for example, a floppy disk or other computer program product inserted in a floppy disk drive or other appropriate drive, or stored on the hard drive, may also be used to operate the controller **460**. The process control program **600** generally

comprises process control software **605** comprising program code to operate the chamber **110** and its components, process monitoring software **610** to monitor the processes being performed in the chamber **110**, safety systems software, and other control software. The computer-readable program **600** may be written in any conventional computer-readable programming language, such as for example, assembly language, C++, Pascal, or Fortran. Suitable program code is entered into a single file, or multiple files, using a conventional text editor and stored or embodied in computer-usable medium of the memory of the computer system **470**. If the entered code text is in a high level language, the code is compiled, and the resultant compiler code is then linked with an object code of precompiled library routines. To execute the linked, compiled object code, the user invokes the object code, causing the CPU **475** to read and execute the code to perform the tasks identified in the program.

Figure 6 is an illustrative block diagram of a hierarchical control structure of a specific embodiment of a process control program **600** according to the present invention. Using a light pen interface, a user enters a process set and chamber number into a process selector program **615** in response to menus or screens displayed on the CRT terminal. The process chamber program **605** includes program code to set the timing, gas composition, gas flow rates, chamber pressure, chamber temperature, RF power levels, support position, heater temperature, and other parameters of a particular process. The process sets are predetermined groups of process parameters necessary to carry out specified processes. The process parameters are process conditions, including without limitations, gas composition, gas flow rates, temperature, pressure, gas energizer settings such as RF or microwave power levels, cooling gas pressure, and wall temperature. In addition, parameters needed to operate the process monitoring program **610** are input by a user into the process selector program **615**. These parameters include known properties of the materials being processed, especially radiation absorption and reflection properties, such as reflectance and extinction coefficients; process monitoring algorithms that are modeled from empirically determined data; tables of empirically determined or calculated values that may be used to monitor the process; and properties of materials being processed on the substrate **105**.

The process sequencer program **620** comprises program code to accept a chamber type and set of process parameters from the process selector program **615** and to control its operation. The sequencer program **620** initiates execution of the process set by passing the particular process parameters to a chamber manager program **625** that controls multiple processing tasks in the process chamber **110**. Typically, the process chamber program **605** includes, among others, a substrate positioning program **630**, a gas flow control program **635**, a gas pressure control program **640**, a gas energizer control program **645**, and a heater control program **650**. Typically, the substrate positioning program **630** comprises program code for controlling chamber components that are used to load the substrate **105** onto the support **130** and optionally, to lift the substrate **105** to a desired height in the chamber **110** to control the spacing between the substrate **110** and the gas outlets **128** of the gas delivery system **120**. The gas flow control program **635** has program code for controlling the flow rates of different constituents of the process gas. The process gas control program **635** controls the open/close position of the safety shut-off valves, and also ramps up/down a gas flow controller to obtain the desired gas flow rate. The pressure control program **640** comprises program code for controlling the pressure in the chamber **110** by regulating the aperture size of the throttle valve **136** in the exhaust system **132** of the chamber **110**. The gas energizer control program **645** comprises program code for setting low and high-frequency RF power levels applied to the process electrodes in the chamber **110** and/or to the inductor coil **160**. Optionally, the heater control program **650** comprises program code for controlling the temperature of the heater element **184** used to resistively heat the support **130** and substrate **105**.

The process monitoring program **610** comprises program code that obtains sample or reference signals from the radiation source **415** or radiation detector **430** and processes the signal according to preprogrammed criteria. Typically, a radiation amplitude or spectrum trace is provided to the controller **460** by an analog to digital converter board in the radiation detector **430**. The process monitoring program **610** may also send instructions to the controller **460** to operate components such as the radiation source **415**, radiation detector **430**, the lens assembly **445**, filters, and other components. The program may also send instructions to the chamber manager

program **605** or other programs to change the process conditions or other chamber settings.

To define the parameters of the process monitoring program **610**, initially, one or more substrates **105** having predetermined thicknesses of material are selected for processing. Each substrate **105** is placed at one time into the process chamber **110** and process conditions are set to process a material or an underlying material on the substrate **105**. Radiation reflected from the substrate and/or emitted from the plasma in the chamber **110** are monitored using one or more radiation detectors **430**. After a series of such traces are developed, they are examined to identify a recognizable change in a property of the trace, which is used as input for the computer program, in the form of an algorithm, a table of values, or other criteria for suitable for evaluating an event in the chamber **110** or a property of the substrate **105**. For example, the process monitoring program **610** may include program code to evaluate a signal corresponding to an intensity of reflected radiation which may be used to detect both an onset and completion of processing of the substrate **105**. As another example, the computer program **600** comprises program code to evaluate first and second signals that correspond to radiation emitted from the plasma and/or reflected from the substrate **105**. In one particular version for determining the endpoint of resist material removal, the computer program **600** may comprise program code to evaluate radiation emitted from the energized gas in the process zone **155**, particularly radiation having a wavelength of about 4835 angstroms.

Thus, the process monitoring program **610** may comprise program codes to monitor a process, as shown in Figure 6. For example, the process monitoring program **610** may comprise radiation source program code **655** to analyze the radiation from the radiation source **415**, radiation detector program code **660** to analyze an incoming signal trace provided by the radiation detector **430** and determine a process endpoint or completion of a process stage when a desired set of criteria is reached, such as when an attribute of the detected signal is substantially similar to a pre-programmed value, and signal evaluation program code **465** to detect errors or anomalies in the monitored signals. The process monitoring program **610** may also be used to detect a property of a material being processed on the substrate **105** such as

a thickness, or other properties, for example, the crystalline nature, microstructure, porosity, electrical, chemical and compositional characteristics of the material on the substrate **105**. The computer program **600** may also be programmed to detect both an onset and completion of processing of the substrate **105**, for example, by
5 detecting a change in amplitude or a rate of change of amplitude of radiation. The desired criteria are programmed into process monitoring program **610** as preset or stored parameters and algorithms. The program **610** may also include program code for modeling a trace of radiation, selecting a feature from the modeled trace or allowing a user to select the feature, storing the modeled trace or the feature,
10 detecting a portion of an incoming signal from a radiation detector **430**, evaluating the measured signal relative to the stored trace or feature, and calling an end of a process stage of the process being performed on the substrate **105** or displaying a measured property of a material on the substrate **105**.

In one version, the process monitoring software comprises program code for continuously analyzing a trace of a measured amplitude of reflected radiation by drawing a box or "window" around the end portion of the trace and back in time, with signal height and time length established in the preprogrammed algorithm. A set of windows may be programmed to detect a valley or peak in the trace of the reflected
15 intensity, trigger on an upward slope to detect a later endpoint, or to trigger on a downward slope to detect an endpoint before a valley in the trace. The first criterion is met when the signal in the trace becomes too steep and exits or moves out of the preprogrammed box ("WINDOW OUT") or when it becomes gradual and enters the box ("WINDOW IN"). Additional windows are sequentially applied on the moving
25 trace to generate the complete set of criteria to make a determination on whether the change in signal measured in the real time trace is an endpoint of the process, such as an onset or completion of the process, a change in the property of the material, or is only noise. The direction of entering or exiting a box may also be specified as part of the preprogrammed input criteria for operating the process monitoring program **610**.
30 Upon detecting an onset or completion of a process, the process monitoring program signals the process chamber program **605** which sends instructions to the controller **460** to change a process condition in a chamber **110** in which the substrate **105** is being processed.

The data signals received by and/or evaluated by the controller **460** may be sent to a factory automation host computer (not shown). The factory automation host computer may comprise a host software program that evaluates data from several systems, platforms or chambers, and for batches of substrates or over an extended period of time, to identify statistical process control parameters. A suitable host software program comprises a WORKSTREAM™ software program available from aforementioned Applied Materials. The factory automation host computer may be further adapted to provide instruction signals to (i) remove particular substrates from the processing sequence, for example, if a substrate property is inadequate or does not fall within a statistically determined range of values, or if a process parameter deviates from an acceptable range; (ii) end processing in a particular chamber, or (iii) adjust process conditions upon a determination of an unsuitable property of the substrate or process parameter. The factory automation host computer may also provide the instruction signal at the beginning or end of processing of the substrate in response to evaluation of the data by the host software program.

While the present invention has been described in considerable detail with reference to certain preferred versions, many other versions should be apparent to those of ordinary skill in the art. For example, deposition of materials may be monitored for endpoint and etch resistant materials other than resist material may be removed from the substrate in the process zone. Therefore, the spirit and scope of the appended claims should not be limited to the description of the preferred versions contained herein.

What is claimed is:

1. A substrate processing method comprising:
 - (a) providing a substrate in a process zone, the substrate comprising etch resistant material over an underlying material;
 - (b) removing the etch resistant material in the process zone;and
 - (c) after (b), providing an energized process gas in the process zone to etch the underlying material.
2. A method according to claim 1 wherein (b) comprises providing an energized stripping gas in the process zone under process conditions selected to substantially remove a layer of etch resistant material.
3. A method according to claim 2 wherein the energized stripping gas comprises an oxygen-containing gas.
4. A method according to claim 3 wherein the energized stripping gas further comprises an oxygen activating gas.
5. A method according to claim 4 wherein the oxygen activating gas comprises a nitrogen-containing gas.
6. A method according to claim 1 wherein the substrate comprises at least two layers of etch resistant material and (b) comprises removing at least one of the layers of etch resistant material.
7. A method according to claim 6 wherein at least one of the layers comprises mask material.
8. A method according to claim 7 further comprising providing an energized process gas to etch apertures in the mask material.

9. A method according to claim 7 further comprising providing an energized process gas in the process zone to etch apertures in the mask material.

10. A method according to claim 7 further comprising, before (b), providing an energized process gas in the process zone to etch apertures in the mask material.

11. A method according to claim 1 wherein the layer comprises silicon and wherein the energized process gas comprises a halogen-containing gas.

12. A method according to claim 11 wherein the energized process gas comprises one or more of CF_4 , C_2F_6 , NF_3 , SF_6 , Cl_2 , Br_2 , HBR , and HCl .

13. A method according to claim 1 wherein the process zone is an energized gas zone in a process chamber.

14. A substrate processing method comprising:

- (a) providing a substrate in a process zone, the substrate comprising a first and a second etch resistant material;
- (b) providing an energized process gas in the process zone to form apertures in the first etch resistant material; and
- (c) removing the second etch resistant material in the process zone.

15. A method according to claim 14 wherein the first etch resistant material comprises mask material.

16. A method according to claim 14 wherein the second etch resistant material comprises photoresist.

17. A method according to claim 14 wherein (b) comprises forming apertures in the first etch resistant material in accordance with a pattern of the second etch resistant material.

18. A method according to claim 14 wherein (c) comprises providing an energized stripping gas in the process zone under process conditions selected to substantially remove the second etch resistant material.

5 19. A method according to claim 18 wherein the energized stripping gas comprises an oxygen-containing gas.

10 20. A method according to claim 14 wherein the substrate comprises a layer under the first and second etch resistant materials and further comprising providing an energized process gas to etch the layer.

21. A method according to claim 14 wherein the substrate comprises a layer under the first and second etch resistant materials and further comprising providing an energized process gas in the process zone to etch the layer.

22. A method according to claim 14 wherein the substrate comprises a layer under the first and second etch resistant materials and further comprising, after (c), providing an energized process gas in the process zone to etch the layer.

23. A method according to claim 22 wherein the layer comprises silicon and wherein the energized process gas comprises a halogen-containing gas.

24. A method according to claim 23 wherein the energized process gas comprises one or more of CF_4 , C_2F_6 , NF_3 , SF_6 , Cl_2 , Br_2 , HBR , and HCl .

25 25. A method according to claim 14 wherein the process zone is an energized gas zone in a process chamber.

26. A substrate processing method comprising:

30 (a) providing a substrate in a process zone, the substrate comprising etch resistant material; and

(b) removing the etch resistant material while detecting radiation emanating from the process zone.

27. A method according to claim 26 further comprising detecting a condition of the radiation related to removal of the etch resistant material.

28. A method according to claim 26 comprising detecting radiation emitted from an energized gas in the process zone.

29. A method according to claim 26 wherein the etch resistant material comprises photoresist and comprising removing the photoresist while detecting a condition of the radiation related to the removal of photoresist.

30. A method according to claim 26 comprising directing radiation onto the substrate and monitoring the radiation reflected by the substrate.

31. A method according to claim 26 comprising providing an energized stripping gas in the process zone under process conditions selected to substantially remove a layer of etch resistant material.

32. A method according to claim 31 further comprising changing process conditions when a characteristic feature of the radiation is detected.

33. A method according to claim 32 wherein the characteristic feature is related to an endpoint of removal of the etch resistant material.

34. A substrate processing method comprising:

- (a) providing a substrate in a process chamber;
- (b) providing an energized process gas in the chamber to process the substrate, thereby depositing process residue on surfaces of the process chamber;
- (c) providing an energized process gas in the chamber to simultaneously remove a material from the substrate and at least partially remove the process residue from the surfaces of the process chamber; and
- (d) after (c), providing an energized process gas in the chamber to further process the substrate.

35. A method according to claim 34 wherein (b) comprises providing an energized process gas in the chamber to form apertures in a material on the substrate.

5 36. A method according to claim 35 wherein (b) comprises forming apertures in a material comprising mask material.

37. A method according to claim 34 wherein (c) comprises removing etch resistant material from the substrate.

10 38. A method according to claim 34 wherein (d) comprises etching a material on the substrate.

39. A substrate processing method comprising:
(a) providing a first substrate in a process chamber;
(b) providing an energized process gas to etch the first substrate, thereby depositing first residue on the surfaces of the process chamber;
(c) providing a second substrate in the process chamber; and
(d) providing an energized process gas to process the second substrate and simultaneously remove the first residue from the surfaces of the process chamber.

40. A method according to claim 39 wherein (d) comprises forming apertures in a material on the second substrate.

25 41. A method according to claim 40 wherein (d) comprises forming second residue on the surfaces of the process chamber.

30 42. A method according to claim 41 further comprising removing the second residue from the surfaces of the process chamber.

43. A method according to claim 41 further comprising removing a material from the second substrate and simultaneously removing the second residue from the surfaces of the process chamber.

5 44. A substrate processing method comprising:
(a) providing a first substrate in a process chamber;
(b) providing an energized process gas to etch the first
substrate, thereby depositing first residue on the surfaces of the process chamber;
(c) providing a second substrate in the process chamber; and
10 (d) providing an energized process gas to at least partially
remove the first residue from the surfaces of the process chamber; and
(e) after (d), removing the second substrate from the chamber.

45. A method according to claim 44 wherein (d) comprises
simultaneously processing the second substrate.

46. A method according to claim 44 wherein (d) comprises providing
an energized process gas comprising a fluorine-containing gas.

20 47. A method according to claim 46 wherein (d) comprises providing
an energized gas comprising one or more of CF_4 , C_2F_6 , SF_6 , and NF_3 .

48. A substrate processing method comprising:
(a) providing a substrate in a process chamber;
25 (b) providing a first energized process gas to etch a material on
the substrate, thereby depositing residue on the surfaces of the process chamber;
(c) providing a second energized process gas to remove
substantially all of the residue deposited in (b) from the surfaces of the process
chamber; and
30 (d) after (c), removing the second substrate from the chamber.

49. A method according to claim 48 wherein (c) comprises
simultaneously processing the substrate.

50. A method according to claim 48 wherein (c) comprises removing a second material from the substrate.

51. A substrate processing method comprising:

- 5 (a) providing a substrate in a process zone, the substrate comprising resist material over mask material;
- (b) providing an energized process gas in the process zone to form apertures in the mask material;
- 10 (c) providing an energized process gas in the process zone to remove the resist material; and
- (d) providing an energized process gas in the process zone to etch a layer under the mask material.

52. A method according to claim 51 wherein (c) comprises providing an energized stripping gas in the process zone under process conditions selected to substantially remove a layer of resist material.

53. A method according to claim 52 wherein the energized stripping gas comprises an oxygen-containing gas.

54. A method according to claim 51 wherein the layer comprises silicon and wherein the energized process gas comprises a halogen-containing gas.




FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 3A




FIG. 3B




FIG. 3C

FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E





FIG. 5






FIG. 6

COMBINED DECLARATION AND POWER OF ATTORNEY

As a below-named inventor, I hereby declare that:

This declaration is of the following type:

- ☒ original
- ☐ divisional
- ☐ continuation
- ☐ continuation-in-part

INVENTORSHIP IDENTIFICATION

My residence, post office address, and citizenship are as stated below next to my name. I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first, and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

TITLE OF INVENTION

"ETCHING A SUBSTRATE IN A PROCESS ZONE"

SPECIFICATION IDENTIFICATION

The specification of which:

- ☒ is attached hereto
- ☐ was filed on _____, under Serial No. _____, executed on even date herewith; or ☐ Express Mail No. _____ (*as Serial No. not yet known*) and was amended on _____ (*if applicable*)
- ☐ was described and claimed in PCT International Application No. _____ filed on _____ and as amended under PCT Article 19 on _____ (*if any*).

ACKNOWLEDGMENT OF REVIEW OF PAPERS AND DUTY OF CANDOR

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose all information I know to be material to patentability in accordance with Title 37, Code of Federal Regulations, § 1.56,

and which is material to the examination of this application; namely, information where there is a substantial likelihood that a reasonable Examiner would consider it important in deciding whether to allow the application to issue as a patent, and

- ☒ In compliance with this duty there is attached an Information Disclosure Statement in accordance with 37 CFR § 1.98.

PRIORITY CLAIM (35 U.S.C. § 119)

I hereby claim foreign priority benefits under Title 35, United States Code § 119, of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America or of any United States Provisional Application(s) listed below, and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed.

- ☒ No such applications have been filed.

- ☐ Such applications have been filed as follows:

- A. Prior foreign/PCT application(s) filed within 12 months (6 months for design) prior to this application, and any priority claims under 35 U.S.C. § 119:

<u>Country/PCT</u>	<u>Application No.</u>	<u>Date Filed</u>	<u>Priority Claimed</u>
--------------------	------------------------	-------------------	-------------------------

☐ Yes ☐ No

- B. All foreign application(s), if any, filed more than 12 months (6 months for design) prior to this U.S. application:

Country:

Application No:

Filing date:

PRIORITY CLAIM (35 U.S.C. § 120)

I hereby claim the benefit under Title 35, United States Code, § 120, of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information that is material to the examination of this application (namely, information where there is substantial likelihood that a reasonable Examiner would consider it important in deciding whether to allow the application to issue as a patent) which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application.

☒ No such applications have been filed.

☐ Such applications have been filed as follows:

<u>Serial No.</u>	<u>Filing Date</u>	<u>Patented</u>	<u>Pending</u>	<u>Abandoned</u>
-------------------	--------------------	-----------------	----------------	------------------

(None)

POWER OF ATTORNEY

I hereby appoint the following attorneys and/or agents to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

Peter J. Sgarbossa	Registration No. 25,610
Donald Verplancken	Registration No. 33,217
Lawrence Edelman	Registration No. 25,226
Michael B. Einschlag	Registration No. 29,301
Joseph Bach	Registration No. 37,771
Raymond Kam-On Kwong	Registration No. 37,165
James C. Wilson	Registration No. 35,412
Sarah J. Brashears	Registration No. 38,087
Robert W. Mulcahy	Registration No. 25,436
Ashok K. Janah	Registration No. 37,487

Send correspondence to: **Direct telephone calls to:**

Applied Materials, Inc.
Patent Department
P.O. Box 450A
Santa Clara, CA 95052

Ashok K. Janah
(415) 538-1555

DECLARATION

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and, further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of **first or sole** inventor: **YUEN, STEPHEN**

Inventor's signature: Stephen Yuen Date: 11/20/00
Residence: Santa Clara, California
Post Office Address: 2435 Ruth Cabral Way
Santa Clara, California 95050
U.S.A.

Country of Citizenship: U.S.A

Full name of **second** inventor: **JAIN, MOHIT**

Inventor's signature: Mohit Kumar Jain Date: 11/20/00
Residence: Santa Clara, California
Post Office Address: 3301 Monroe Street, #3
Santa Clara, California 95051
U.S.A.

Country of Citizenship: India

Full name of **third** inventor: **LILL, THORSTEN B.**

Inventor's signature: Thorsten B. Lill Date: 11/20/00
Residence: Sunnyvale, California
Post Office Address: 880 E. Fremont Ave. #634
Sunnyvale, California 94087
U.S.A.

Country of Citizenship: Germany

(Declaration ends with this page)